

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 426 470 A2

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: 90311968.3

(51) Int. Cl.⁵: **G03F 7/32**

(22) Date of filing: **01.11.90**

(30) Priority: **02.11.89 JP 287107/89**
03.11.89 JP 286957/89

(43) Date of publication of application:
08.05.91 Bulletin 91/19

(84) Designated Contracting States:
DE GB

(71) Applicant: **KONICA CORPORATION**
26-2, Nishishinjuku 1-chome, Shinjuku-ku
Tokyo 160(JP)

(72) Inventor: **Nogami, Akira, Konica Corporation**
1 Sakura-machi, Hino-shi
Tokyo(JP)
Inventor: **Uehara, Masafumi, Konica**
Corporation
1 Sakura-machi, Hino-shi
Tokyo(JP)
Inventor: **Shimura, Kazuhiro, Konica**
Corporation
1 Sakura-machi, Hino-shi
Tokyo(JP)

(74) Representative: **Ellis-Jones, Patrick George**
Armine et al
J.A. KEMP & CO. 14 South Square Gray's Inn
London WC1R 5LX(GB)

(54) **Method for developing a waterless light-sensitive lithographic plate.**

(57) A method of developing a waterless light-sensitive lithographic printing plate comprising a support and, provided thereon, a light-sensitive layer comprising a diazo compound, and a silicone gum or silicone rubber layer, which comprises contacting the plate with a developer comprising an organic carboxylic acid or salt thereof, water, and at least one of a sulfite and a surfactant.

EP 0 426 470 A2

METHOD FOR DEVELOPING A WATERLESS LIGHT-SENSITIVE LITHOGRAPHIC PLATE

FIELD OF THE INVENTION

This invention relates to a method of developing a waterless light-sensitive lithographic plate and, more particularly, to a method of developing a waterless light-sensitive lithographic plate, which is high in development rate, low in environmental pollution, odor production and inflammability and excellent in safety.

BACKGROUND OF THE INVENTION

10

There have so far been well-known waterless light-sensitive lithographic plates including, for example, those comprising each a support coated thereon with a light-sensitive layer and an ink-repellent layer in order.

15 This type of waterless light-sensitive lithographic plates are developed after they are exposed image-wise to light. The developers applicable thereto include, for example, the organic solvent type developers such as those detailed in Japanese Patent Examined Publication No. 54-26923/1979, with which waterless light-sensitive lithographic plates are developed.

When using this type of the developer, the developments may be made at a satisfactory development rate on one hand, however, there raise the problems of inflammability, safety, or environmental pollution caused by the organic solvents on the other hand.

In the meantime, as for the developers prepared by taking the inflammability, safety and hygiene into consideration, the well-known aqueous type developers including those described in, for example, Japanese Patent Publication Open to Public Inspection -hereinafter referred to as Japanese Patent O.P.I. Publication- Nos. 60-140243/1985 and 61-275759/1986. The techniques described therein are low in inflammability and excellent in safety because the developers contain water. However, these developers have the problem that the development efficiency is seriously deteriorated especially when processing a great number of plate materials with an automatic processor, because the development rate thereof is not high enough.

The present inventors have seriously studied on the above-mentioned problems and, resultingly, they have discovered that the problems can be solved by containing an organic carboxylic acid and at least one of a sulfite and a surfactant.

SUMMARY OF THE INVENTION

35

It is, therefore, an object of the invention to provide a method of developing a waterless light-sensitive lithographic plate, which is high in development rate, low in environmental pollution, odor production and inflammability, and excellent in safety.

40

DETAILED DESCRIPTION OF THE INVENTION

45 The above-mentioned object of the invention can be achieved in a method of developing a waterless light-sensitive lithographic printing plate having a support and, provided thereon, a light-sensitive layer comprising a diazo resin and a silicone gum layer with a developer, wherein said developer comprises an organic carboxylic acid or salt thereof, water, and at least one of a sulfite and a surfactant.

The invention will now be detailed below.

50 The components of the developers applicable to the invention for developing waterless light-sensitive lithographic plates include an organic carboxylic acid, a sulfite and/or a surfactant. The components thereof will be detailed.

The organic carboxylic acid applicable to the invention includes, preferably, an aliphatic or aromatic carboxylic acid having 6 to 20 carbon atoms.

The typical examples of the aliphatic carboxylic acids each having 6 to 20 carbon atoms include

caproic acid, enanthic acid, caprylic acid, pelargonic acid, capric acid, lauric acid, mistylic acid, palmitic acid, and stearic acid. Among them, the particularly preferable examples thereof include an alkane acid having 8 to 12 carbon atoms. Besides, either an aliphatic acid having a double bond in the carbon chain thereof or those having a branched carbon chain may also be used.

5 The above-given aliphatic carboxylic acids should preferably be used in the form of the sodium, potassium or ammonium salts thereof so that the water-solubility of the aliphatic carboxylic acids may be enhanced.

The aromatic carboxylic acids include the compounds having a benzene ring, a naphthalene ring or an anthracene ring substituted with an carboxyl group. The typical examples of the compounds include
10 benzoic acid, o-chlorobenzoic acid, p-o-chlorobenzoic acid, o-hydroxybenzoic acid, p-hydroxybenzoic acid, o-aminobenzoic acid, p-aminobenzoic acid, 2,4-dihydroxybenzoic acid, 2,5-dihydroxybenzoic acid, 2,6-dihydroxybenzoic acid, 2,3-dihydroxybenzoic acid, 3,5-dihydroxybenzoic acid, gallic acid, 1-hydroxy-2-naphthoic acid, 3-hydroxy-2-naphthoic acid, 2-hydroxy-1-naphthoic acid, 1-naphthoic acid and 2-naphthoic acid. Among them, an aromatic carboxylic acid is particularly useful. The above-given aromatic carboxylic
15 acids should preferably be used in the form of the sodium, potassium or ammonium salts thereof so that the water-solubility thereof can be enhanced.

The organic carboxylic acids or salts thereof should be added into the developers of the invention, in an amount within the range of, preferably, 0.1 wt% to 10 wt% and, preferably, 0.5 wt% to 4 wt%.


The sulfite usefully applicable to the invention includes, for example, sodium sulfite, potassium sulfite,
20 lithium sulfite and ammonium sulfite.

The sulfite is contained in the developer in an amount within the range of 0.1 to 10% by weight.

The surfactant preferably useful includes, for example, an anionic or nonionic surfactant.

The anionic surfactant includes, for example; a higher alcohol having C₈ to C₂₂; sulfates such as sodium lauryl alcohol sulfate, sodium cetyl alcohol sulfate, ammonium lauryl alcohol sulfate, 'T-Pole B-81', a
25 brand-name, manufactured by Shell Chemical Co., and secondary sodium alkylsulfate; aliphatic alcohol phosphates such as the sodium salts of cetyl alcohol phosphate; alkylaryl sulfonates such as sodium dodecylbenzene sulfonate, sodium isopropyl-naphthalene sulfonate, sodium dinaphthalene sulfonate and sodium metanitrobenzene sulfonate; alkylamide sulfonates such as

30



35

and the sulfonic acid salts of dibasic aliphatic acid esters, such as sodium sulfosuccinic acid dioctyl ester and sodium sulfosuccinic acid dihexyl ester. Among them, the sulfonic acid salts should preferably be used in particular.

The content of the anionic surfactant is within the range of 1 wt% to 30 wt% and, preferably, 3 wt% to
40 15 wt%, each to the whole amount of a developer used.

Various types of the nonionic surfactants may be used therein.

In other words, the nonionic surfactants may roughly be classified into two types, namely, a polyethylene glycol and a polyhydric alcohol. In the invention, any one of these two types of them may be used. From the viewpoint of obtaining a greater effect, a polyethylene glycol is preferably used as a nonionic
45 surfactant.

Among them, it is preferable to use a nonionic surfactant having three or more ethylene oxide groups, i.e., -CH₂CH₂O-groups, and a value of hydrophilic lipophile balance, abbreviated to HLB, of 5 to 20 and, preferably, 8 to 20.

Among the nonionic surfactants, those having both of an ethyleneoxy group and a propylene oxide
50 group are particularly preferable. Further, among them, those having an HLB value of 8 to 20 are preferable.


The preferable examples of the nonionic surfactants applicable to the invention include the compounds represented by the following formulas 1 through 8.

55


Formula 1




Formula 2




Formula 3




Formula 4




Formula 5



Formula 6



Formula 7



Formula 8



In Formulas 1 through 8, R represents a hydrogen atom or a monovalent organic group. The organic groups include, for example; an alkyl group which may have a straight-chained or branched substituent having 1 to 30 carbon atoms, such as an aryl group, e.g., a phenyl group; an alkylcarbonyl group comprising an alkyl component that is the above-mentioned alkyl group; and a phenyl group which may

have a substituent such as a hydroxyl group or such an alkyl group as mentioned above.

In the above-given formulas, a, b, c, m, n, x and y are each an integer of 1 to 40.

Now, the typical examples of the non-ion type surfactants applicable to the invention will be given below.

5 Namely, polyethylene glycol, polyoxyethylene lauryl ether, polyoxyethylene nonyl ether, polyoxyethylene cetyl ether, polyoxyethylene stearyl ether, polyoxyethylene behenyl ether, polyoxyethylene polyoxypropylene cetyl ether, polyoxyethylene polyoxypropylene behenyl ether, polyoxyethylene nonylphenyl ether, polyoxyethylene octylphenyl ether, polyoxyethylene stearyl amine, polyoxyethylene oleyl amine, polyoxyethylene stearic acid amide, polyoxyethylene oleic acid amide, polyoxyethylene castor oil, 10 polyoxyethylene abietic ether, polyoxyethylene lanolin ether, polyoxyethylene monolaurate, polyoxyethylene monostearate, polyoxyethylene glyceryl monoaurate, polyoxyethylene glycermonostearate, polyoxyethylene propyleneglycol monostearate, oxyethyleneoxypropylene block polymer, distyrenophenol polyethylene oxide adduct, tribenzylphenol polyethylene oxide adduct, octylphenol polyoxyethylene polyoxypropylene adduct, glycerol monostearate, sorbitan monolaurate, and polyoxyethylene sorbitan monolaurate. 15

The weight average molecular weight of the non-ion type surfactants applicable to the invention is within the range of, preferably, 300 to 10000 and, particularly, 500 to 5000. The concentration of the non-ion type surfactants in a developer is within the range of 0.001 to 20 wt%. When it is less than 0.001 wt%, any noticeable effects can be obtained. The particularly preferable concentration of the non-ion type surfactants 20 on as developer is within the range of 0.1 to 10 wt%.

The non-ion type surfactants may be used independently or in combination.

In the invention, sulfites and the surfactants may be used independently or in combination.

The water-contents thereof is within the range of 20 wt% to 97 wt% and, preferably, 50 wt% to 95 wt%.

As the developers applicable to the invention, an alkaline aqueous type developers may preferably be 25 used. The pH values of the developers are not lower than 10 and, preferably, within the range of pH 11.5 to 13.0.

For the purpose of making the developers alkaline to have a pH of not lower than 10, it is allowed to use, for example; silicates such as sodium silicate and potassium silicate; inorganic alkali agents such as potassium hydroxide, sodium hydroxide, lithium hydroxide, tertiary sodium phosphate, secondary sodium 30 phosphate, tertiary potassium phosphate, secondary potassium phosphate, tertiary ammonium phosphate, secondary ammonium phosphate, sodium metasilicate, sodium bicarbonate, sodium carbonate, potassium carbonate, and ammonium carbonate; organic alkali agents such as a mono- or di-triethanolamine and tetraalkyl hydroxide; and organic ammonium silicate. Among them, silicates are preferably used.

Silicates are contained in an amount within the range of 0.1 to 20% by weight in the developer of the 35 invention.

It is preferable that the developers of the invention further contain an organic solvent in a proportion within the range of 0.1 to 20 wt%.

The preferable organic solvents include at least one selected from the group consisting of alcohols such as methanol, ethanol and benzyl alcohol; amines such as methylamine, ethylamine and diethanolamine; 40 ethylene glycols such as diethylene glycol and triethylene glycol; and propylene glycols such as α -propylene glycol and β -propylene glycol. Benzyl alcohol or propylene glycol is more preferable.

To the developers applicable to the invention, the following additives may be added; namely, neutral salts such as NaCl, KCl and KBr each described in Japanese Patent O.P.I. Publication No. 58-75152/1983; chelating agents such as EDTA and NTA each described in Japanese Patent O.P.I. Publication No. 58- 45 190952/1983; Complexes such as $[\text{CO}(\text{NH}_3)_6]\text{Cl}$ and $\text{COCl}_2 \cdot 6\text{H}_2\text{O}$ each described in Japanese Patent O.P.I. Publication No. 59-121336/1984; anionic or amphoteric surfactants such as sodium alkyl naphthalene sulfonate and N-tetradecyl-N,N-dihydroxyethyl betaine each described in Japanese Patent O.P.I. Publication No. 50-51324/1975; non-ion type surfactants such as tetramethyl decynediol described in U.S. Patent No. 4,374,920; cationic polymers such as quaternary methyl chloride compounds of p-dimethylaminomethyl 50 polystyrene described in Japanese Patent O.P.I. Publication No. 55-95946/1980; amphoteric high molecular electrolytes such as a copolymer of vinylbenzyltrimethyl ammonium chloride and sodium acrylate described in Japanese Patent O.P.I. Publication No. 56-142528/1981; reducible inorganic salts such as sodium sulfite described in Japanese Patent O.P.I. Publication No. 57-192952/1982; Inorganic lithium compounds such as lithium chloride described in Japanese Patent O.P.I. Publication No. 58-59444/1983; organic lithium 55 compounds such as lithium benzoate described in Japanese Patent Examined Publication No. 50-34442/1975; organic metal surfactants each containing silica or titanium described in Japanese Patent O.P.I. Publication No. 59-75255/1984; organic boron compounds described in Japanese Patent O.P.I. Publication No. 59-84241/1984; and quaternary ammonium salts such as tetraalkyl ammonium oxide described in

In the light-sensitive layers suitably treated with the developers of the invention, a diazo compound is used

10

30

35

10

45



55

The silane coupling agents or the silicone cross coupling agents applicable to the invention are the

silane compounds represented by the following formula:



wherein n is an integer of 1 to 3; R represents an alkyl group, an aryl group, an alkenyl group, or the monovalent group combined thereof, provided, these groups may have a functional group such as those of halogen, amine, hydroxy, alkoxy, aryloxy and thiol; X represents a substituent such as those of -OH, -OR², -OAc,



-Cl, -Br, and I, wherein R² and R³ represent each the same as the above-denoted R, and R² and R³ may be the same with or the different from each other; and Ac represents an acetyl group.

In other words, the silicone rubber useful in the invention can be obtained through the condensation reaction of the silicone*base polymer with a silicone cross coupling agent such as those given above.


The silane coupling agents applicable to the invention include, typically, HN[(CH₂)₃Si(OMe)₃]₂, vinyltriethoxysilane, Cl(CH₂)₃Si(OMe)₃, CH₃Si(OAc)₃, HS(CH₂)₃Si(OMe)₃, and vinyltris(methylethylketoxime) silane.

The above-mentioned silicone rubber are available on the market as commercial articles such as YE-3085 manufactured by Toshiba Silicone Co. The other useful silicone rubber may be obtained through the reaction of the foregoing base*polymer with silicone oil having a repetition unit represented by the following formula II, the addition reaction thereof with a silicone base*polymer in which about 3% of R is a vinyl group, or the reaction of the silicone oil with each other.

Formula II

30

35



wherein R is synonymous with R representing the substituent of the polymers in Formula I; m is an integer of not less than 2; and n is an integer of 0 or not less than 1.

For obtaining the silicone rubber through the cross coupling reaction such as mentioned above, the cross coupling reaction is carried out with a catalyst. The catalysts applicable thereto include, for example, the organic carboxylates of metals such as tin, zinc, cobalt, lead, calcium and manganese. To be more concrete, tin dibutylaurate, tin(II) octate or cobalt naphthenate, or chloroauric acid.

For the purpose of obtaining a silicone rubber having a resistance against friction produced in printing operations by improving the strength of the silicone rubber, a filler may be mixed in. Silicone rubber mixed in advance with a filler therein are available on the market in the forms of a silicone rubber stock and a silicone rubber dispersion. In the case where it is preferable that a silicone rubber layer is obtained by a coating operation as in the invention, an RTV or LTV silicone rubber dispersion is preferably used. The examples thereof include, for example, the silicone rubber dispersions for paper coating such as Syl Off 23, SRX-257 and SH237, manufactured by Toray Silicone Co.

In the invention, it is preferable to use a condensation cross coupling type silicone rubber.

For further improving the adhesive property, it is preferable to contain a silane coupling agent having an amino group into a silicone rubber layer.

The preferable silane coupling agents include, for example;

(a) H₂NCH₂CH₂NH(CH₂)₃Si(OCH₃)₃,

(b) H₂NCE₂CH₂NH(CH₂)₃Si(OCH₃)₂(CH₃), and

(c) $\text{H}_2\text{N}(\text{CH}_2)_3\text{Si}(\text{OEt})_3$

The silicone rubber layer applicable to the invention is further allowed to contain a small amount of a photosensitizer.

The silicone rubber layer applicable to the invention is coated and then dried on a light-sensitive layer, after the silicone rubber is dissolved in a suitable solvent.

The support of the invention should preferably have a flexibility suitable for setting it to an ordinary lithographic printer and a resistance against a load applied when carrying out a printing operation. The supports include, for example, a sheet of metal, paper, plastic film or glass, each plated or vacuum evaporated thereon with a metal such as chromium, zinc, copper, nickel, aluminium and iron; and a sheet of paper coated with a resin or pasted with a foil of a metal such as aluminium.

Among them, one of the preferable supports is an aluminium plate.

There is no special limitation to the treatments on the supports themselves for improving the above-mentioned adhesive property thereof, and the treatments include, for example, a variety of the surface roughening treatments.

The supports are allowed each to have a primer layer. The primer layers include, for example, those of a polyester resin, a vinyl chloride-vinyl acetate copolymer, an acryl resin, a vinyl chloride resin, a polyamide resin, a polyvinyl butyral resin, an epoxy resin, an acrylate type copolymer, a vinyl acetate type copolymer, a phenoxy resin, a polyurethane resin, a polycarbonate resin, a polyacrylonitrile butadiene, and a polyvinyl acetate. The above-given primer layers may be added by a compound capable of producing an acid when the above-mentioned exposure is made, or a dye discolored or faded by an acid.

The anchoring agents constituting the above-mentioned primer layer include, for example, the above-mentioned silane coupling agent and a silicone primer and, besides, an organic titanate is also useful for this purpose.

The thicknesses of each layers constituting the lithographic plates of the invention are as follows: The thicknesses of the supports are within the range of 50 to 400 μm and, preferably, 100 to 300 μm ; the thicknesses of the light-sensitive layers are within the range of 0.05 to 10 μm and, preferably, 0.5 to 5 μm ; and the thicknesses of the silicone rubber layers are within the range of 0.1 to 10 μm and, preferably, 0.5 to 2 μm .

In the invention, if required, a protective layer may be provided onto the silicone rubber layer.

As the methods in which the above-mentioned light-sensitive lithographic printing plates are developed with the developer of the invention, it is allowed to use the methods such as a shower development method and a dipping development method, each having been well-known in the developments of light-sensitive lithographic printing plates such as a PS plate; provided, however, it is preferable to rub the plate surface with a brush or a sponge either in the course of a development or in one of the post processing steps of the development, such as a dyeing or washing step.

The developers are generally used with circulating them and replenishing a part of them when it is fatigued. On the other hand, there is also a method in which a substantially fresh developer is supplied onto a plate every time when processing light-sensitive lithographic plates to develop the plate and the developer is then throw it away.

The developing temperatures are within the range of 15°C to 45°C and, preferably, 25°C to 35°C. The developing time is within the range of 15 seconds to 150 seconds and, preferably, 20 seconds to 60 seconds.

Examples

Now, the invention will be detailed with reference to the following examples. It is, however, to be understood that the invention shall not be limited thereto.

Examples 1 to 6 and Comparative Examples 1 to 3

The following primer layer was coated on a 0.3 μm -thick aluminium plate and was then heat-treated at 200°C for 2 minutes, so that a primer layer having a dried thickness of 3 μm could be prepared.

Composition of the primer layer		
5	Polyurethane resin, Sanprene LQ-T 1331, manufactured by Sanyo Kasei Industries Co.	100 wt*parts
	Block isocyanate, Takenate B 830, manufactured by Takeda Pharmaceutical Industrial Co.	20 wt*parts
	Epoxy phenol urea resin, ST 9372, manufactured by Kansai Paint Co.	8 wt*parts
	Dimethylformamide	725 wt*parts

10 On the resulting primer layer, the following light-sensitive layer was successively coated so that the light-sensitive layer could be 2 μ m in dry thickness.

Composition of light-sensitive layer		
15	Hexafluorophosphate of the paraformaldehyde condensate of p-diazodiphenyl amine	0.5 wt*parts
	A copolymer of N-(4-hydroxyphenyl)methacrylamide: acrylonitrile: ethylacrylate:methacrylic acid = 27:33:41:6 in the ratio by weight; Acid value = 80	5 wt*parts
	Tartaric acid	0.05 wt*parts
	Victoria Pure Blue BOH, a dye, manufactured by Hodogaya Chemical Industries Co.	0.1 wt*parts

25 Next, a 10% n-hexane diluted silicone solution having the following composition was coated on the light-sensitive layer so that the dry thickness of the coat could be 2 μ m.

Silicone rubber layer		
30	Dimethyl polysiloxane, having a molecular weight of about 80000	100 wt*parts
	Methyltriacetoxysilane	5 wt*parts
	Tin dibutylacetate	0.2 wt*parts

35 An original document film was brought into close contact with the resulting plate, and it was exposed to a 2 KW high-pressure mercury vapour lamp for 30 seconds.

Next, the resulting printing plate was rubbing-developed with a sponge and with the developer shown in Table-1, until an image was reproduced. The results thereof are shown in Table-1.

Table-1

		Composition of Developer	Part by weight	Developing time required
45	Inven- tion	Potassium sulfite	2.5	4.8 minutes
		Benzoic acid	3.0	
		Potassium hydroxide	1.5	
		Water	93.0	
50	Inven- tion	Sodium dibutyl-naphthalenesul- fonate	2.5	4.5 minutes
		Benzoic acid	3.0	
		Potassium hydroxide	1.5	
		Water	93.0	

Table-1 (cot'd)

		Composition of Developer	Part by weight	Developing time required
5				
10	Inventive Example-3	Sodium dibutyl-naphthalenesulfonate p-tert-butylbenzoate Potassium hydroxide Water	2.5 3.0 1.5 93.0	3.8 minutes
15	Inventive Example-4	Sodium dibutyl-naphthalenesulfonate Caprylic acid Potassium hydroxide Water	2.5 3.0 1.5 93.0	5.5 minutes
20	Inventive Example-5	Sodium laurylsulfate Sodium 2-hydroxy-3-naphthoate Benzyl alcohol Potassium hydroxide Water	1.8 3.0 0.4 0.8 94.0	4.0 minutes
25	Inventive Example-6	Polyoxyethylene lauryl ether p-tert-butylbenzoate Potassium hydroxide Potassium sulfite Potassium metasilicate Water	0.1 1.4 1.0 2.0 3.0 92.5	3.0 minutes
30	Comparative Example-1	p-tert-butylbenzoate Potassium hydroxide Water	3.0 1.5 95.5	7.0 minutes
35	Comparative Example-2	Sodium dibutyl-naphthalenesulfonate Potassium hydroxide Water	3.0 0.7 96.3	7.0 minutes
40	Comparative Example-3	Potassium sulfite Potassium hydroxide Water	3.0 0.3 96.3	7.5 minutes

As is obvious from Table-1, the developers No. 1 to No. 6 of the invention have almost no odor and are high in safety, because they do not contain any organic solvent. They are also high in development rate, although they are of the aqueous type. On the other hand, the developers No. 1 to No. 3 of the comparative examples are not satisfactory in development rate and not suitable for a mass and continuous processing treatment, though they have a cold odor and are good in safety.

Example 7

An original document film was superposed on the same waterless printing plate as used in Example 1 and an exposure was then made for 50 seconds to a 3 KW metal halide lamp from a distance of 70 cm. Next, the exposed light-sensitive lithographic printing plate was processed at random for 50 seconds with the following developer B. When trying a printing operation by putting the resulting light-sensitive lithographic printing plate on a printer, an excellent printed matter without having any stained background could be obtained.

Developer B	
Propylene glycol	10 wt*parts
β -anilinoethanol	1 wt*parts
p-tert-butylbenzoate	3 wt*parts
Emulgen 147, a nonionic surfactant, manufactured by Kao Corporation	0.1 wt*parts
Potassium sulfite	2 wt*parts
An aqueous potassium silicate solution, having a SiO ₂ content of 26 wt% and a K ₂ O content of 14 wt%	2 wt*parts
Potassium hydroxide	2 wt*parts
Water	80 wt*parts

Claims

1. A method of developing a waterless light-sensitive lithographic printing plate comprising a support and, provided thereon, a light-sensitive layer comprising a diazo compound, and a silicone gum or silicone rubber layer, which comprises contacting the plate with a developer comprising an organic carboxylic acid or salt thereof, water, and at least one of a sulfite and a surfactant.
2. The method of claim 1, wherein the developer comprises an organic carboxylic acid or salt thereof, water, a sulfite and a surfactant.
3. The method of claim 1 or 2, wherein the developer has a pH of not less than 10.
4. The method of any one of the preceding claims, wherein the organic carboxylic acid or salt thereof is an aliphatic or aromatic carboxylic acid having from 6 to 20 carbon atoms or a sodium, potassium or ammonium salt thereof.
5. The method of claim 4, wherein the organic carboxylic acid or salt thereof is caproic acid, enanthic acid, caprylic acid, pelargonic acid, capric acid, lauric acid, mistyic acid, palmitic acid, stearic acid, benzoic acid, o-chlorobenzoic acid, p-chlorobenzoic acid, o-hydroxybenzoic acid, p-hydroxybenzoic acid, o-aminobenzoic acid, p-aminobenzoic acid, 2,4-dihydroxybenzoic acid, 2,5-dihydroxybenzoic acid, 2,6-dihydroxybenzoic acid, 2,3-dihydroxybenzoic acid, 3,5-dihydroxybenzoic acid, gallic acid, 1-hydroxy-2-naphthoic acid, 3-hydroxy-2-naphthoic acid, 2-hydroxy-1-naphthoic acid, 1-naphthoic acid or 2-naphthoic acid, or a sodium, potassium or ammonium salt thereof.
6. The method of any one of the preceding claims, wherein the developer comprises the carboxylic acid or salt thereof in an amount of from 0.1 to 10% by weight relative to the total weight of the developer.
7. The method of any one of the preceding claims, wherein the sulfite is sodium sulfite, potassium sulfite, lithium sulfite, or ammonium sulfite.
8. The method of any one of the preceding claims, wherein the developer comprises the sulfite in an amount of from 0.1 to 10% by weight relative to the total weight of the developer.
9. The method of any one of the preceding claims, wherein the surfactant is a nonionic surfactant.
10. The method of claim 9, wherein the nonionic surfactant is a polyethylene glycol.
11. The method of claim 10, wherein the polyethylene glycol has three or more ethylene oxide groups and an HLB value of from 5 to 20.
12. The method of claim 10, wherein the polyethylene glycol has an ethylene oxide group and a propylene oxide group and a HLB value of from 8 to 20.
13. The method of any one of claims 9 to 12, wherein the nonionic surfactant is contained in the developer in an amount of from 0.001 to 20% by weight relative to the total weight of the developer.
14. The method of claim 13, wherein the nonionic surfactant is contained in the developer in an amount of from 0.1 to 10% by weight relative to the total weight of the developer.
15. The method of any one of the preceding claims, wherein the water is contained in the developer in an amount of from 20 to 97% by weight relative to the total weight of the developer.
16. The method of claim 15, wherein the water is contained in the developer in an amount of from 50 to 95% by weight relative to the total weight of the developer.
17. The method of any one of the preceding claims, wherein the developer further comprises silicates in an amount of from 0.1 to 20% by weight relative to the total weight of the polymer.

18. The method of any one of the preceding claims, wherein the developer further comprises an organic solvent in an amount of from 0.1 to 20% by weight relative to the total weight of the polymer.

19. The method of claim 18, wherein the organic solvent is benzyl alcohol or a propylene glycol.

5

10

15

20

25

30

35

40

45

50

55

(19)



Europäisches Patentamt
European Patent Office
Office européen des brevets



(11) Publication number:

0 426 470 A3

(12)

EUROPEAN PATENT APPLICATION

(21) Application number: **90311968.3**

(51) Int. Cl.⁵: **G03F 7/32**

(22) Date of filing: **01.11.90**

(30) Priority: **02.11.89 JP 287107/89**
03.11.89 JP 286957/89

(43) Date of publication of application:
08.05.91 Bulletin 91/19

(84) Designated Contracting States:
DE GB

(88) Date of deferred publication of the search report:
12.02.92 Bulletin 92/07

(71) Applicant: **KONICA CORPORATION**
26-2, Nishishinjuku 1-chome, Shinjuku-ku
Tokyo 160(JP)

(72) Inventor: **Nogami, Akira, Konica Corporation**
1 Sakura-machi, Hino-shi
Tokyo(JP)
Inventor: **Uehara, Masafumi, Konica**
Corporation
1 Sakura-machi, Hino-shi
Tokyo(JP)
Inventor: **Shimura, Kazuhiro, Konica**
Corporation
1 Sakura-machi, Hino-shi
Tokyo(JP)

(74) Representative: **Ellis-Jones, Patrick George**
Armine et al
J.A. KEMP & CO. 14 South Square Gray's Inn
London WC1R 5LX(GB)

(54) **Method for developing a waterless light-sensitive lithographic plate.**

(57) A method of developing a waterless light-sensitive lithographic printing plate comprising a support and, provided thereon, a light-sensitive layer comprising a diazo compound, and a silicone gum or silicone rubber layer, which comprises contacting the plate with a developer comprising an organic carboxylic acid or salt thereof, water, and at least one of a sulfite and a surfactant.

EP 0 426 470 A3



European
Patent Office

EUROPEAN SEARCH REPORT

Application Number

EP 90 31 1968

DOCUMENTS CONSIDERED TO BE RELEVANT

Category	Citation of document with indication, where appropriate, of relevant passages	Relevant to claim	CLASSIFICATION OF THE APPLICATION (Int. Cl.5)
X	EP-A-0 279 630 (KONICA) " the whole document " "	1-19	G 03 F 7/32
X	EP-A-0 056 138 (HOECHST AG) " the whole document " "	1,4-6, 9-16	
A	EP-A-0 067 001 (KONICA)		
The present search report has been drawn up for all claims			TECHNICAL FIELDS SEARCHED (Int. Cl.5)
			G 03 F
Place of search		Date of completion of search	Examiner
The Hague		04 December 91	HAENISCH U.P.
CATEGORY OF CITED DOCUMENTS			
X : particularly relevant if taken alone			
Y : particularly relevant if combined with another document of the same category			
A : technological background			
O : non-written disclosure			
P : intermediate document			
T : theory or principle underlying the invention			
E : earlier patent document, but published on, or after the filing date			
D : document cited in the application			
L : document cited for other reasons			
& : member of the same patent family, corresponding document			